

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 January 2002 (24.01.2002)

PCT

(10) International Publication Number
WO 02/06581 A1

(51) International Patent Classification⁷: **D06M 15/263**,
15/423, D06N 3/04

(21) International Application Number: PCT/US01/20164

(22) International Filing Date: 25 June 2001 (25.06.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/615,506 13 July 2000 (13.07.2000) US

(71) Applicant: **MILLIKEN & COMPANY** [US/US]; Legal
Department (M-495), P.O. Box 1926, Spartanburg, SC
29303 (US).

(72) Inventors: **ARNOTT, Robert, C.**; 173 Stribling Circle,
Spartanburg, SC 29301 (US). **GOLD, J., Phillip**; 52 Hills-
borough Drive, Greenville, SC 29615 (US).

(74) Agent: **MOSES, Thomas, L.**; Milliken & Company, Legal
Department (M-495), P.O. Box 1926, Spartanburg, SC
29304 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

WO 02/06581 A1

(54) Title: METHOD OF TREATING A ROLLER SHADE MATERIAL

(57) **Abstract:** A roller shade material, such as 100 % polyester, is passed through a bath, so that both sides of the material are coated by the bath. In a preferred embodiment, the bath includes an acrylic polymer finish, and a melamine-formaldehyde cross-linking agent. The acrylic polymer preferably is approximately 45 % solid, and comprises about 47 % to 48 % of the bath by weight. The cross-linking agent preferably comprises about 2.5 % of the bath by weight, and is about 80% solid material. The bath should have a pH in the basic range between about 7 and 9.5, and the preferred base used to adjust the pH is N,N-Diethylethanolamine. Optional compounds that may be added to the bath include an anti-stick compound and a defoaming agent. This treatment produces a roller shade having a clear coating that allows the color, texture and weave of the substrate to show, without hindering the ability of light to pass through the material. Further, and more importantly, the coating provides dimensional stability for the roller shade, which reduces or eliminates the tendency of the material to distort by bowing, cupping, or cambering, and preserves the hand and feel of the product.

ROLLER SHADE TREATMENT AND METHOD

Background of the Invention

1. Field of the Invention

5 The present invention is related to a method of treating roller shades to provide superior hanging characteristics. More specifically, the roller shade material is padded in a bath containing an acrylic polymer finish and a cross-linking resin in a basic mixture, so that the weight of the dried coating comprises between 18% and 40% of the total dry weight of the coated material.

10 One problem that has been traditionally associated with roller shades is the tendency for the material to distort when the shade is in the unrolled, extended position. Often, the material has a tendency to cup or bow, which means the shade is configured in a mild C shape, in one direction or the other. Another distortion characteristic of the material is the tendency for the material to torque or camber, which means that the shade tends to twist either in a
15 clockwise or counter-clockwise direction with respect to the top edge of the shade.

Several attempts have been made to overcome these problems. One approach has been to use heavy gauge fabric that has fewer tendencies to
20 distort. The drawback to this approach is that it is sometimes desirable to provide a lighter gauge fabric for roller shades, particularly in cases where it is desirable to allow some light to pass through the shade. Another proposed solution has been to attach a heavy base rod or other base member to the bottom edge of the roller shade to prevent the distortion, which has met with
25 limited success. While this approach prevents the bottom edge from cupping or bowing, the sides of the material still tend to distort, and the base member does not prevent, or even reduce, the tendency for the material to camber. Yet another proposed solution to the distortion problem is to coat the material with a heavy layer of polymeric material, which destroys the hand and feel of the
30 product.

Therefore, it would be desirable to provide a coating for roller shades that prevents or minimizes distortion tendencies, and which does not negatively

affect the hand and feel of the product. Further, it would be desirable to provide a method for treating roller shades that may be performed with minimal steps, and also which is inexpensive to implement and run. Moreover, it would be desirable to provide a roller shade having a clear coating that provides
5 dimensional stability for the material, without limiting the transmission of light through the product.

2. Description of the Prior Art

All patents cited are incorporated herein by reference in their entirety. The following patents are generally directed to polymeric coatings for various
10 substrates.

U.S. Patent number 4,276,212, issued to Khanna, et al., teaches a high solids coating composition containing at least 50% by weight of a binder of film-forming constituents in which the constituents are of:

- 15 (a) an acrylic polymer that has a number average molecular weight of about 500-4,500, a hydroxyl content of at least 2% by weight, a glass transition temperature of about -20° C to 20° C, and optionally contains a chain transfer agent, and is of an alkyl methacrylate, a hydroxy alkyl acrylate or a hydroxy alkyl methacrylate, and optionally, an alkyl acrylate or styrene
- 20 (b) an alkylated melamine formaldehyde cross-linking agent; the composition is particularly useful as an exterior finish for automobiles, trucks, airplanes and can be used as an appliance finish and for coil coatings.

U.S. Patent number 4,396,672, issued to Adesko, is directed to a substrate having a cured color coat layer of a pigmented coating composition
25 and a cured clear coat layer firmly adhered to the color coat layer; wherein the layers are formed from a high solids coating composition containing at least 40% by weight of a binder of film-forming constituents in which the constituents are of:

- 30 (1) an acrylic polymer of styrene or methyl methacrylate or mixtures thereof, an alkyl acrylate or an alkyl methacrylate and a hydroxyl alkyl acrylate or methacrylate,
- (2) a polyester polyol, and

- (3) an alkylated melamine formaldehyde cross-linking agent and optionally, an acid catalyst;

the clear coat/color coat finish is particularly useful as an exterior finish for automobiles, trucks, and airplanes.

5 U.S. Patent number 5,721,309, issued to Sharma, et al., teaches a water based coating composition that provides a stain resistant layer which adheres well to a substrate and is resistant to chemical attack by common household cleaning solvents such as isopropyl alcohol. The coating composition is aqueous based and incorporates a cross-linkable acrylic polymer latex, an amino resin
10 cross-linking agent and a cross-linking catalyst. The polymer, cross-linking agent and catalyst are dispersed and/or solubilized in an aqueous medium. The coating composition is particularly well suited for application to flexible vinyl chloride polymer substrates to produce upon curing and drying a stain resistant, easily cleanable laminate.

15 None of the prior art, however, teaches a treatment for roller shades, comprising a bath including an acrylic polymer finish and a cross-linking resin in a basic medium without a catalyst, where the roller shade material is padded through the bath, and where the final dry weight of the coating comprises 18% to 40% of the dry weight of the coated material.

20

Objects of the Invention

Accordingly, an important object of the present invention is to provide a roller shade treatment that provides dimensional stability and reduces or eliminates the tendency for the roller shade material to distort while hanging in
25 an unrolled, extended position.

Another important object of the present invention is to provide a clear coating for a roller shade that allows the color, texture and weave of the substrate to show, without hindering the ability of light to pass through the material.

30 Yet another important object of the present invention is to provide a roller shade treatment that is durable and allows the roller shade to be either spot cleaned or cleaned by immersion in soap and water.

Still another important object of the present invention is to provide a roller shade having acceptable hand and feel, and which provides resistance to fraying on the edges.

Another important object of the present invention is to provide a novel
5 roller shade produced by a treatment process that is inexpensive to implement and run, and which overcomes some of the problems associated with prior art roller shades and processes for treating them.

These and other features, aspects, and advantages of the present invention will become better understood with reference to the following
10 description and appended claims.

Detailed Description of the Preferred Embodiment

In a preferred embodiment, a roller shade material, such as 100% polyester, is passed through a bath, so that both sides of the material are coated
15 by the bath. The bath includes an acrylic polymer finish, which is sold commercially under the trade name POLYCRYL 7F7 by Rohm & Haas, and an alkylated melamine – formaldehyde cross-linking agent commercially available from B.F. Goodrich under the trade name AEROTEX M3. The acrylic polymer emulsion is preferably approximately 45% solid, and comprises about 40%–55%
20 of the bath, and preferably 47% to 48% of the bath. The AEROTEX cross-linking agent comprises about 80% solids as received, and makes up approximately 1%-5% of the bath, and preferably comprises 2.5%-3.5% of the bath. The bath has a pH in the basic range of about 7 to 9, and the preferred base used to adjust the pH is N,N-Diethylethanolamine, commercially sold by BASF.

25 Optional compounds that may be added to the bath include an anti-stick compound, used to prevent fabric from sticking to the pins or the tenter frame during the drying and curing step. The preferred anti-stick compound is emulsified lubricant, sold under the trade name ANTISTICK N, by Relco Chemical Co. Defoamers may be used as well, including DEFOAMER 908 from
30 Milliken Chemical.

It is to be understood, however, that many permissible variations may be made in the bath composition. For example, although the cross-linking agent

has been described as a melamine-formaldehyde resin, it should be noted that any suitable cross-linking agent may be used. Also, other polymers may be used in lieu of acrylic, including styrene/acrylic, polyurethane, polyvinyl acetate, and polyvinyl chloride. Ammonia, or other bases, may be substituted for the N,N-Diethylethanolamine.

In the manufacturing process, the roller shade material, which is preferably of a weight ranging from approximately 1.8 oz/yd² to 8 oz/yd², is padded through the bath. Then the material is nipped through a pair of rollers to squeeze the excess liquid from the fabric. The material is then dried and cured, preferably using a tenter frame, at a drying temperature of about 385°F. The drying and curing steps strengthen the dimensional stability of the fabric when polyester fabric is used, because the polyester fabric is heat set. The dry add-on or coating ultimately comprises between 18% and 40% of the weight of the dry coated fabric. In a most preferred embodiment, the dry add-on coating comprises between 20% and 25% of the weight of the dry coated fabric.

In the following Example, a comparative test was performed on a product manufactured in accordance with the preferred embodiment of the present invention, and was also performed on other, similar products currently available in the marketplace. The test, hereinafter referred to as the Heat Chamber test, was performed to measure the distortion characteristics of a variety of roller shades. The purpose of the test was to simulate the high temperatures that may occur in a closed up dwelling or motor home, that may contain a roller shade, and measure the effect of the heat on the performance and hanging characteristics of the roller shade material.

EXAMPLE 1

Table 1 shows the results of a distortion comparison test between the Milliken products, manufactured in accordance with the present invention, and competing products manufactured by Montreal Woolens.

Table 1

	Milliken: Satin	Montreal Woolens: Jacquard	Montreal Woolens: Dobbie	Milliken: Silk Slub
Ends/Inch	61	101	49	149
Picks/Inch	62	40	49	63
Weight (oz/yd ²)	2.86	6.21	5.54	4.70
Blend	100% polyester	100% polyester	100% polyester	100% polyester
Warp Yarn	1/180/34	200	600	n/a
Fill Yarn	1/150/34	400	400	n/a
Selvedge Type	Fringe	Tuck	Tuck	n/a
Distortion (inches)	0	5/8	1/4	1/16
Handleometer measurements (Warp/Fill)	186/75	829/>1000	673/710	207/645

The test was run by placing 12 inch by 12 inch square samples of each fabric, hung with the warp direction running vertically, in an oven at a temperature of 170 ° F for 4 hours in the extended position. Then, the roller shade fabrics were removed from the oven and hung and measured. A straight ruler was placed against both sides of the roller shade, establishing a plane. A measurement was taken to determine the farthest distance between the plane and a corresponding point on the fabric. Higher distance measurements indicate higher levels of distortion for the roller shade fabrics, and conversely, lower distance measurements indicate lower, more desirable, levels of distortion. These measurements were provided for bowed, cupped, or cambered roller shades.

The handleometer test was conducted by using blade to push a 4 inch by 4 inch sample of each material downwardly into a 10 mm slot. The test

measured the number of grams necessary to bend the fabric and push the sample to a specific depth into the slot. This test was performed to measure the force necessary to bend the fabric in the warp direction and in the fill direction.

It can be seen from Table 1 that the coating provides dimensional stability
5 that cannot be produced by competitive products in the art. Further, no other treatments for roller shade material provide proper hanging properties in combination with acceptable handleometer numbers within the ranges of 185-650 in the warp direction, and 75-650 in the fill direction.

Although the present invention has been described in considerable detail
10 with reference to certain preferred versions thereof, other versions are possible. Therefore, the spirit and scope of the appended claims should not be limited to the description of the preferred versions contained herein. All features disclosed in this specification may be replaced by alternative features serving the same, equivalent or similar purpose, unless expressly stated otherwise. Thus, unless
15 expressly stated otherwise, each feature disclosed is one example only of a generic series of equivalent or similar features.

Claims

What is claimed is:

1. A method for applying a finish coating to a roller shade material, said
5 method comprising the steps of:
 providing a bath having an acrylic polymer and a cross linking agent in a
 mixture having a pH above 7.0;
 applying said bath to a roller shade material through a padding process so
 that the dry weight of the coating ultimately falls between the range of 18% to
10 40% of the total weight of the coated substrate; and
 drying said substrate.
2. The method set forth in claim 1, wherein said acrylic polymer is Polycryl
7F7.
- 15 3. The method set forth in claim 1, wherein said cross-linking agent is
Aerotex M3.
4. The method set forth in claim 1, wherein said bath further includes N,N-
20 Diethylethanolamine.
5. The method set forth in claim 1, wherein said bath further includes an
anti-stick compound.
- 25 6. The method set forth in claim 1, wherein the dry weight of the coating
ultimately falls between the range of 20% to 25% of the total weight of the coated
substrate.
7. A roller shade treated in accordance with the method set forth in claim 1.
- 30 8. A roller shade treated in accordance with the method set forth in claim 2.

9. A roller shade treated in accordance with the method set forth in claim 3.
10. A roller shade treated in accordance with the method set forth in claim 4.
- 5 11. A roller shade treated in accordance with the method set forth in claim 5.
12. A roller shade treated in accordance with the method set forth in claim 6.
13. A coated fabric that exhibits a distortion of less than $\frac{1}{4}$ inch under the heat
10 chamber test.
14. The coated fabric set forth in claim 13, wherein said coated fabric exhibits
handleometer measurements in the range of 185-650 in the warp direction, and
75-650 in the fill direction.
- 15 15. A roller shade fabric having a coating comprising an acrylic polymer and a
cross-linking agent.
16. The roller shade fabric set forth in claim 15, wherein said acrylic polymer
20 is Polycryl 7F7.
17. The roller shade fabric set forth in claim 15, wherein said cross-linking
agent is Aerotex M3.
- 25 18. The roller shade fabric set forth in claim 15, wherein the dry weight of the
coating ultimately falls between the range of 20% to 25% of the total weight of
the coated fabric.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/20164

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 D06M15/263 D06M15/423 D06N3/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 D06M D06N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 040 329 A (HORNSCHUCH AG K) 25 November 1981 (1981-11-25) claims 2,3,7,11	7-18
X	US 4 645 704 A (HELLWIG MANFRED) 24 February 1987 (1987-02-24) column 3, line 8 - line 16 column 3, line 59 - line 68 column 4, line 67 - column 5, line 3	7-18
X	GB 1 578 071 A (PFERSEE CHEM FAB) 29 October 1980 (1980-10-29) page 1, line 27 - line 38 page 4, line 61 - line 65 page 7, line 5 - line 10	7-18
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents:**

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family.

Date of the actual completion of the international search

15 November 2001

Date of mailing of the international search report

22/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Fiocco, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/20164

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	NL 9 100 429 A (MIN SHU WANG) 1 October 1992 (1992-10-01) page 1, line 21 - line 34 page 5, line 39 -page 6, line 6	13-17
A	EP 0 955 404 A (ESPRIADA GMBH) 10 November 1999 (1999-11-10) paragraph '0001! paragraph '0015!	1-18
A	AU 648 738 A (MEREDITH ANN ARNOLD;KELVIN HAROLD ARNOLD) 28 April 1994 (1994-04-28) page 3, line 1 - line 23 page 6, line 7 - line 10	1-18

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/20164

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0040329	A	25-11-1981	DE 3016191 A1 AT 3662 T EP 0040329 A2	29-10-1981 15-06-1983 25-11-1981
US 4645704	A	24-02-1987	EP 0193636 A1 AT 45402 T DE 3664938 D1 EP 0194564 A2	10-09-1986 15-08-1989 14-09-1989 17-09-1986
GB 1578071	A	29-10-1980	DE 2607151 A1 DE 2610372 A1 BE 851652 A1 CH 626219 A FR 2343079 A1 IT 1081480 B NL 7700131 A	25-08-1977 15-09-1977 22-08-1977 13-11-1981 30-09-1977 21-05-1985 23-08-1977
NL 9100429	A	01-10-1992	NONE	
EP 0955404	A	10-11-1999	DE 29808044 U1 EP 0955404 A1	30-07-1998 10-11-1999
AU 648738	A	28-04-1994	AU 648738 A3	28-04-1994

THIS PAGE BLANK (USPTO)